

## PRODUCT DATA SHEET

Date: 05/10/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

58# Primeglos<sup>TM</sup> \*\* LiftOff<sup>TM</sup> \*\* 40# liner

Item#: 0048575

	TRIMI	ESS P	ROGR	<b>AMS</b>	
--	-------	-------	------	------------	--

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"

Recommended for hand-applied applications only.

Facestock: **58# Primeglos**<sup>TM</sup> A 58# bright white sheet featuring high CD tensile and MD tear,

great die cutting and stripping characteristics, and good stiffness for dispensing. Low Parker Print and exceptional gloss make this sheet printable with all standard flexo and letterpress inks.

**Typical Value** 

Basis Weight:  $58 \#/3300 \text{ ft}^2$  Caliper: 3.0 mils Tensile MD/CD: 35 / 18 #/inch

Gloss: 72%

Tear MD/CD: 43 / 56 grams
Opacity: 88.5%
Parker Print: .9 microns
Brightness: 90%

Adhesive: **LiftOff**<sup>TM</sup> A hot melt removable adhesive featuring excellent long-term removability.

Good initial adhesion and clean removability allows for use on a variety of

surfaces.

**Typical Value** 

Coat Weight:  $10 \#/3300 \text{ ft}^2$ Coat Weight:  $14.8 \text{ grams/m}^2$ 

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 7

Loop Tack, oz.:

Service Temperature: -20 to 140 °F

Minimum Application Temperature: 30 °F Shear (1000g): 10 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

 Basis Weight:
 41 #/3000 ft²

 Caliper:
 2.5 mils

 Tensile MD/CD:
 34 / 21 #/inch

 Tear MD/CD:
 34 / 36 grams

 Opacity:
 69 max%

**Total Product Caliper:** 6.1 mils

Product Basis Weight Per MMSI: 238.11 #

**Shelf Life:** 12 month(s) when stored at 72° F. 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023