



PRODUCT DATA SHEET

Date: 05/10/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

SafeTE™ C1S Cover-up ** BP-164 ** 40# liner

Item#: 0043080

----- TRIMLESS PROGRAMS -----

Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core
Domino (UV Inkjet)	Troy, Ohio	2.5 K	3"	3"
Screen Americas (UV Inkjet)	Troy, Ohio	5 K	3"	3"
Flexo	Troy, Ohio	10 K	4"	3"
	New York	5 K	3"	3"
	New York	10 K	4"	3"

Facestock: **SafeTE™ C1S Cover-up**

A C1S paper designed to provide a high level of destructibility when combined with the appropriate adhesive. An opaque barrier coat applied to the backside of the facestock adds opacity for hiding underlying text or graphics. This facestock has sufficient tensile and tear properties to permit good performance on press.

Typical Value

Basis Weight:	61 #/3300 ft ²
Caliper:	3.6 mils
Tensile MD/CD:	34 / 16
Tear MD/CD:	53 / 66 grams
Opacity:	90%
Sheffield Smoothness:	125 SFU
Parker Print:	1.07 microns

Adhesive: **BP-164**

A general purpose hot melt adhesive with excellent quick-stick properties. This adhesive exhibits excellent adhesion to a broad range of packaging surfaces and has improved die cutting and stripping attributes compared to other hot melt rubber based adhesives.

Typical Value

Coat Weight:	14 #/3300 ft ²
Coat Weight:	20.72 grams/m ²
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	63
Loop Tack, oz.:	97
Service Temperature:	-50 to 150 °F
Minimum Application Temperature:	40 °F
Shear (1000g):	456 minutes

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

	Typical Value
Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 6.7 mils

Product Basis Weight Per MMSI: 252.84 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 02/06/2024